

RATINGS / APPROVALS

250°C - 600 Volts - UL Style 3637 / CSA AWM Class I A/B FT2

CONSTRUCTION

Conductors

22 AWG — 8 AWG Stranded nickel-plated copper - 2% (Other conductor materials available)

Insulating System


Composite Extruded Silicone Rubber with intermediate fiberglass reinforcement

Standard Color Coding

Iron Oxide Red with Colored Markings

CHARACTERISTICS

- Outperforms Braided Silicone products:
 - ~ Eliminates braid fraying, flowering and shrink back.
 - ~ Virtually eliminates skin irritation.
 - \sim Significantly reduces airborne fiberglass contaminants traditionally found in high volume processing.
 - ~ Superior flexibility.
 - ~ Color stable at elevated temperatures.
 - ~ Low smoke.
- Silicone formulations suitable for UV, ozone, moisture exposure.
 Not suited for immersed applications.
- Suitable for applications to -60°C.





RAMIN SIL. A. BLEND

Silicone Rubber

SPECIFICATIONS



SIL-A-BLEND 250C/600V

Part No.	Awg. Size	# Strands	Outer Dia. inches	Outer Dia. mm	Wgt - lbs per 1000 ft	Wgt - kg per km	UL	CSA
NMA20P007	20	7	0.110	2.80	8.01	11.91	3637	AWM I A/B FT2
NMA18P019	18	19	0.117	2.98	10.12	15.06	3637	AWM I A/B FT2
NMA16P026	16	26	0.129	3.27	13.90	20.68	3637	AWM I A/B FT2
NMA 14P041	14	41	0.143	3.63	19.33	28.77	3637	AWM I A/B FT2
NMA 12P065	12	65	0.162	4.11	28.36	42.20	3637	AWM I A/B FT2
NMA10P105	10	105	0.216	5.50	47.27	70.35	3637	AWM I A/B FT2
NMA08P133	8	133	0.299	7.58	80.13	119.24	3637	AWM I A/B FT2

Standard conductor: Nickel Plated Copper - 2%

Consult factory for alternate conductor and stranding options.

