



Scotch-Weld™ DP760

Product Data Sheet

Updated : February 2009
Supersedes: June 2001

Product Description

DP760 epoxy adhesive is a non-sag, two-part room temperature curing adhesive designed for use when high temperature resistance is required.

Physical Properties

Not for Specification Purposes

	BASE	ACCELERATOR
Base	Toughened Epoxy	Modified Amine
Colour	White	White
Specific Gravity (approx.)	1.26	0.82
Mix Ratio		
By Volume	100	50
By Weight	100	32
Viscosity	Non-sagging paste	Non-sagging paste
Worklife at 23°C (min)		
5 g	60-80	
10 g	45-60	
20 g	35-40	

Typical Performance

Characteristics

Not for specification purposes

Overlap Shear Strength (MPa)

Test conditions	Cure cycle 1	Cure cycle 2	Cure cycle 3
- 55 ± 3°C	19.4 (C)	17.4 (C)	21.9 (C)
23 ± 2°C	28.2 (C)	29.1 (C)	30.4 (C)
80 ± 2°C	24.1 (C)	24.2 (C)	25.9 (C)
120 ± 2°C	16.2 (C)	16.1 (C)	15.4 (C)
150 ± 2°C	10.4 (C)	11.9 (C)	10.3 (C)
175 ± 3°C	7.6 (C)	7.3 (C)	7.5 (C)
205 ± 3°C	4.9 (C)	5.2 (C)	5.3 (C)
230 ± 3°C	2.9 (C)	3.0 (C)	3.5 (C)

Test method EN 2243-1

Overlap shear specimens were constructed using 1.6 mm thick 2024 T3 clad aluminum with the surface prepared using the optimized FPL etch.

Typical Performance Characteristics

Not for specification purposes

Roller (Bell) Peel Strength (N/25mm)

Cure cycle 1	Cure cycle 2	Cure cycle 3
184	154	159

Test method EN 2243-2

Roller (Bell) peel specimens were constructed using 1.6 and 0.5 mm thick 2024 T3 clad aluminum with the surface prepared using the optimized FPL etch

Cure cycles :

7 days at $23 \pm 2^{\circ}\text{C}$ under a pressure of 100 kPa the first 24 hours

24 hours at $23 \pm 2^{\circ}\text{C}$ under a pressure of 100 kPa followed by a 60 min post cure at $80 \pm 3^{\circ}\text{C}$

120 min at $65 \pm 3^{\circ}\text{C}$ under a pressure of 100 kPa.

150 μm diameter glass beads were used to control glue line thickness

Environmental Resistance

Not for specification purposes

Overlap Shear Strength (MPa)

Conditions	Test results
Control (23°C / 50% RH)	28.8 (Cohesive)
D.I. water at 23°C	29.1 (Cohesive)
150°C dry heat	21.4 (Cohesive)
JP4 fuel at 23°C	28.9 (Cohesive)
Engine oil at 23°C	27.8 (Cohesive)
Hydraulic oil at 23°C	27.2 (Cohesive)
50°C ; $\geq 95\%$ relative humidity	24.9 (Cohesive)
5 % salt spray at 35°C	28.1 (Cohesive)*
* Denotes no corrosion under the glue line	

Test method EN 2243-1

Long term humidity resistance
Not for specification purposes

Overlap Shear Strength (MPa)

Test conditions	Initial Performance		Performance after 750 h at 70°C ≥ 95 % RH	
	Clad AA	Bare AA	Clad AA	Bare AA
- 55 ± 3°C	18.8 (Cohesive)	18.6 (Cohesive)	22.9(Cohesive)	Not tested
23 ± 2°C	28.7 (Cohesive)		24.8 (Cohesive)	19.0 (Adhesive/ Cohesive)
80 ± 2°C	22.9 (Cohesive)	21.9 (Cohesive)	16.5 (Cohesive)	18.0 (Cohesive)
120 ± 2°C	16.5 (Cohesive)	14.6 (Cohesive)	8.3 (Adhesive/Cohe sive)	12.8 (Cohesive)
150 ± 2°C	10.4 (Cohesive)	10.0 (Cohesive)	5.6 (Adhesive/Cohe sive)	9.0 (Cohesive)
175 ± 3°C	7.9 (Superficial cohesive)	6.9 (Cohesive)	3.7 (Adhesive/Cohe sive)	Not tested

Test method EN 2243-1

Table denotes typical results obtained on 1.6 mm thick clad and bare 2024 T3 aluminum alloy with the surface prepared by the optimized FPL etch method after curing for 7 days at 23 C. 150 µm glass beads were used to control the glue line thickness.

Thermal properties

The glass transition temperature (Tg) was determined using Perkin/Elmer DSC7 analyzer with a heating rate of 10°C/min. Second heat values given. Mid-point : 145-150 °C

Compression strength and Young's modulus

Data generated from a cast block of material (12.5 x 12.5 x 25 mm) and curing for 24 hours at 23+/-3°C followed by a 60 minutes post-cure at 80+/-3°C. Specific gravity of the cured material was measured as 1.11 at 23 °C

Compression strength (MPa)	Young's modulus (MPa)
23 +/- 2°C : 78.8	23 +/- 2°C : 5972
80 +/- 2°C : 48.7	80 +/- 2°C : 4930
120 +/- 2°C : 36.8	120 +/- 2°C : 3633
150 +/- 3°C : 24.2	150 +/- 3°C : 2350

Additional Product Information

Work Life:

After mixing, the mixture remains workable for a time before it becomes too viscous to properly wet the surface to which it is applied.

The work life and rate of cure are both greatly affected by temperature and to some extent humidity, curing faster as temperature and humidity are raised.

Once mixed, the adhesive should be used within 1 hour.

Equipment :

3M Scotch-Weld™ DP760 is supplied in a dual syringe plastic cartridge designed to fit the EPX™ applicator system.

Contact your 3M representative for assistance in selecting application equipment to suit your specific needs.

Clean Up:

Excess adhesive can be cleaned up prior to curing with 3M Solvent No.2.

Note: 3M Solvent No.2 is flammable. When using solvents for clean up it is essential that the correct safety precautions are observed.

A thoroughly cleaned, dry, grease-free surface is essential for maximum performance.

Cleaning methods which will produce a break free water film on metal surfaces are generally satisfactory

Surface Preparation

For high strength structural bonds, paint, oxide films, oils, dust and all other surface contaminants must be completely removed. The level of surface preparation will depend on the required bond strength and environmental resistance required.

Storage Conditions

Rotate stock on a "first in - first out" basis. When stored at room temperature, shelf life is 6 months. 2 years shelf life applies if the material is stored at -18°C.

Shelf Life

6 months from date of dispatch by 3M when stored in the original carton at 4°C and 50% relative humidity.

Precautionary Information

Refer to product label and Material Safety Data Sheet for health and safety information before using the product.

Refer to the Technical Bulletin for information about "Application Guide"

For information please contact your local 3M Office.
www.3M.com

For Additional Information

To request additional product information or to arrange for sales assistance, call 0870 60 800 50 Address correspondence to: 3M 3M United Kingdom PLC 3M House, 28 Great Jackson Street, Manchester, M15 4PA

Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M is a trademark of the 3M Company.

3M United Kingdom PLC
3M House,
28 Great Jackson Street,
Manchester,
M15 4PA

Product Information :
Tel 0870 60 800 50
Fax 0870 60 700 99

3M Ireland
3M House, Adelphi Centre,
Upper Georges Street,
Dun Laoghaire, Co. Dublin,
Ireland

Customer Service :
Tel (01) 280 3555
Fax (01) 280 3509