

## PRODUCT DATA

Date: April 2011

Information Sheet No.: 02770-25

# EVO-STIK 9517

## WATER BASED ADHESIVE

EVO-STIK 9517 is a ready for use, fast setting; single part curing polyvinyl acetate based emulsion.

### RECOMMENDED USE

EVO-STIK 9517 is a multipurpose, water resistant adhesive, which conforms to the D3 requirements of EN204 and it also meets the requirements of BS4071 Part 5 sustained load resistance.

EVO-STIK 9517 is suitable for general assembly and lamination on particleboard and MDF.

### BONDING INSTRUCTIONS

#### Working conditions:

Minimum temperature for use	12°C
Ambient temperature (warehouse, wood, laminates, adhesive)	18 - 20°C
Humidity of wooden substrates	8 - 12%

#### Coating weight:

Flat lamination, paper (single face coverage)	20 - 70g/m <sup>2</sup>
Flat lamination, HPL, thick foils (single face coverage)	100 - 200g/m <sup>2</sup>
Assembly (single face coverage)	150 - 200g/m <sup>2</sup>

#### Assembly time:

4 - 8 min

#### Pressure:

Wood on wood	2 - 5 bar (kgf/cm <sup>2</sup> )
Laminates on wood	1 - 2 bar (kgf/cm <sup>2</sup> )

#### Pressing time (minimum):

Wood on wood at 20°C	10 - 15 min
Assemblies with one face preheated	2 - 3 min
Laminates on wood at 20°C	20 - 30 min
Laminates on wood at 80°C	3 - 4 min

#### Stabilisation:

Before machining	2 hours (minimum)
Complete setting of adhesive	at least 24 hours
D3 water resistance	at least 1 week

#### Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, or its liability for fraud, or fraudulent misrepresentation, or any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Bostik Ulverscroft Road, Leicester, LE4 6BW England. Tel: +44 (0) 1785 272625 Fax: +44 (0) 116 253 1943

[www.Bostik.co.uk](http://www.Bostik.co.uk)

# PRODUCT DATA

Date: April 2011

Information Sheet No.: 02770-25

## SURFACE PREPARATION

- Substrates to be bonded should be perfectly clean, dry and free from dust and grease.
- For laminations, surfaces should be homogeneous and flat.
- Assemblies should be precise in order to avoid thick adhesive lines (0.2 - 0.3mm max.).
- Wood should be allowed to condition for several days in the workshop atmosphere (15 - 20°C) before bonding. Its relative humidity should be approx. 10 - 20%.

## APPLICATION

- For lamination apply an even coat of adhesive to one of the substrates by roller coater, brush or spatula.
- For assembly applications we recommend that both surfaces should be coated.
- Coating weight depends on substrate, porosity, open time and ambient temperature.

### General features

Flat lamination	100 - 240 g/m <sup>2</sup>
Panelling, edge jointing	200 - 350 g/m <sup>2</sup>
Other (notice/tenon, tongue/groove)	coat both sides

## ASSEMBLY

- The parts to be bonded should be brought together immediately after application whilst the adhesive is still wet.
- The maximum open time depends on the substrate porosity, ambient temperature and coating weight. A guideline is given on page 1.

## PRESSING

- After assembly pressure should be maintained during the adhesive's initial setting period, using conventional pressing methods such as presses, vices, jigs clamps or dead loads. Refer to the pressure values given on page 1. This is not necessary for finger joints.
- Pressing time depends on such variables as ambient temperature and humidity, coating weight, porosity of substrates and dimensions of assemblies. Reference values are given on page 1 but a test specimen will allow this to be calculated.
- Pressing time can be reduced by heating one substrate to be bonded before pressing at room temperature. We recommend pre-heating of the surface (1 - 2 minutes at 80°C).
- Hot pressing should only be recommended for double sided flat lamination.

## GENERAL PRECAUTIONS

- Do not add anything to the adhesive to modify its properties
- Provided contact with iron is avoided the adhesive should not cause staining.
- After each use close the container tightly to avoid skin formation.
- Coating equipment and tools can be cleaned with warm water, before the adhesive has dried out.
- For health, safety and disposal please refer to the material safety data sheet.

---

### Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, or its liability for fraud, or fraudulent misrepresentation, or any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Bostik Ulverscroft Road, Leicester, LE4 6BW England. Tel: +44 (0) 1785 272625 Fax: +44 (0) 116 253 1943

[www.Bostik.co.uk](http://www.Bostik.co.uk)

# PRODUCT DATA

Date: April 2011

Information Sheet No.: 02770-25

## TYPICAL CHARACTERISTICS

Physical Form:	Viscous liquid
Colour:	White
Viscosity (Brookfield RVT, 20rpm, at 23°C):	Approx. 12000mPa.s
Specific Gravity:	Approx. 1.10

## PACKAGING

Please refer to Customer Service Department for current package sizes.

## STORAGE

Store in original packaging between 5 and 30°C. **Protect from frost.** After prolonged storage stir well before use.

## SHELF LIFE

Under the above storage conditions, 12 months closed in its original packaging

## MATERIAL SAFETY DATA

For further information refer to the relevant Health and Safety Data Sheet.

---

### Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, or its liability for fraud, or fraudulent misrepresentation, or any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Bostik Ulverscroft Road, Leicester, LE4 6BW England. Tel: +44 (0) 1785 272625 Fax: +44 (0) 116 253 1943

[www.Bostik.co.uk](http://www.Bostik.co.uk)