

PRODUCT DATA SHEET

Seal Coat®Clear Urethane Coating, 11 Wt Oz No. 18411

Product Description

Applications

Brand

Net Fill

UPC Code

Case Weight

I 2 of 5 Code

Appearance

Plastic Safe

Coverage

Dielectric Strength

It provides a conformal polyurethane coating that insulates electrical equipment and seals out water and moisture. This product allows clear visualization of whatever it is sprayed upon. It is an excellent insulator of PC boards, since it allows visualization of circuit paths. It dries quickly to a hard, durable, flexible film.

On motor windings, terminals, bus bars, commutator ends, stator coils, and PC boards

Unit Package Description 16 Ounce Aerosol CRC **Generic Description 1** Urethane Coating 11 Wt Oz 078254184111 Unit Dimensions 8.1H x 8.3W x 11.1D in Units Per Case 12 **Case Dimensions** 8.6H x 8.4W x 11.3D in Cases Per Pallet 133 11 lbs 30078254184112 **Clear Viscous Liquid** -4°F Flash point (F) Flash point (C) -20°C Flammability Class - CPSC **Extremely Flammable** Spec Gravity Concentrate 0.717 Yes **Evaporation Rate** Fast 72 Hours Dry Time - Fully Dry Dry Time - Tack Free 15 to 30 Minutes 20 to 25 Sq Ft

1,300 Volts/Mil

Last revised: 2/27/2017 Page 1 of 2



Customer Care: 800-556-5074

Technical Assistance: 800-521-3168

www.crcindustries.com

professionals serving industrial, electrical, aviation, automotive and marine markets. CRC is ISO 9001:2008 certified

CRC*, K&W*, Sta-Lube*, Marykate* and products denoted with * and ™ are trademarks of CRC Industries, Inc.

CRC Industries is a worldwide leader in the production of specialty chemicals for maintenance and repair

and adheres to the strictest guidelines for quality in all facets of research, development and production.



PRODUCT DATA SHEET

Working Temp (F)	-90 to 250°F
Working Temp (C)	-67.8 to 121.1°C
Propellant	Hydrocarbon
Aerosol Flammability Level	111
DOT Proper Shipping Name	Aerosols, Flammable, Limited Quantity
VOC % (Federal)	63.9
VOC g/L (Federal)	457.8
VOC Lbs./Gal. (Federal)	3.8
VOC Category	Aerosol Coating: Electrical Coating
MIR Limit (EPA)	None
MIR Limit (CA)	2.0
MIR Value	1.46
Removal (How To)	Extremely difficult to remove, scraping is recommended.






Last revised: 2/27/2017 Page 2 of 2



Customer Care: 800-556-5074 Technical Assistance: 800-521-3168 www.crcindustries.com



CRC*, K&W*, Sta-Lube*, Marykate* and products denoted with * and ™ are trademarks of CRC Industries, Inc.