

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

SECTION 1: Identification of the substance/mixture and of the company/undertaking

1.1 Product identifier

Trade name : ARALDITE® 2014-1 GB RESIN

1.2 Relevant identified uses of the substance or mixture and uses advised against

Use of the Substance/Mixture : Epoxy constituents

1.3 Details of the supplier of the safety data sheet

Company : Huntsman Advanced Materials (Europe)BVBA
Address : Everslaan 45
3078 Everberg
Belgium
Telephone : +41 61 299 20 41
Telefax : +41 61 299 20 40

E-mail address of person responsible for the SDS : Global_Product_EHS_AdMat@huntsman.com

1.4 Emergency telephone number

Emergency telephone number : EUROPE: +32 35 75 1234
France ORFILA: +33(0)145425959
ASIA: +65 6336-6011
China: +86 20 39377888
+86 532 83889090
India: + 91 22 42 87 5333
Australia: 1800 786 152
New Zealand: 0800 767 437
USA: +1/800/424.9300

SECTION 2: Hazards identification

2.1 Classification of the substance or mixture

Classification (REGULATION (EC) No 1272/2008)

Skin irritation, Category 2	H315: Causes skin irritation.
Serious eye damage, Category 1	H318: Causes serious eye damage.
Skin sensitisation, Category 1	H317: May cause an allergic skin reaction.
Chronic aquatic toxicity, Category 2	H411: Toxic to aquatic life with long lasting effects.

2.2 Label elements

Labelling (REGULATION (EC) No 1272/2008)

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Hazard pictograms :



Signal word : Danger

Hazard statements	:	H315	Causes skin irritation.
		H317	May cause an allergic skin reaction.
		H318	Causes serious eye damage.
		H411	Toxic to aquatic life with long lasting effects.

Precautionary statements	:	Prevention:	
		P261	Avoid breathing mist or vapours.
		P273	Avoid release to the environment.
		P280	Wear protective gloves/ eye protection/ face protection.
		Response:	
		P305 + P351 + P338 + P310	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a POISON CENTER/doctor.
		P333 + P313	If skin irritation or rash occurs: Get medical advice/ attention.
	P362 + P364	Take off contaminated clothing and wash it before reuse.	
	Disposal:		
	P501	Dispose of contents and container in accordance with all local, regional, national and international regulations.	

Hazardous components which must be listed on the label:

Bisphenol A epoxy resin

bisphenol F-epoxy resin

Butanedioldiglycidyl ether

terephthalic acid diglycidylester

Additional Labelling:

EUH205 Contains epoxy constituents. May produce an allergic reaction.

2.3 Other hazards

This substance/mixture contains no components considered to be either persistent, bioaccumulative and toxic (PBT), or very persistent and very bioaccumulative (vPvB) at levels of 0.1% or higher.
No information available.

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

SECTION 3: Composition/information on ingredients

3.2 Mixtures

Hazardous components

Chemical name	CAS-No. EC-No. Registration number	Classification (REGULATION (EC) No 1272/2008)	Concentration (% w/w)
4,4'-Isopropylidenediphenol, oligomeric reaction products with 1-chloro-2,3-epoxypropane	25068-38-6 500-033-5 01-2119456619-26	Eye Irrit. 2; H319 Skin Irrit. 2; H315 Skin Sens. 1; H317 Aquatic Chronic 2; H411	30 - 60
Formaldehyde, oligomeric reaction products with 1-chloro- 2,3-epoxypropane and phenol	9003-36-5 500-006-8 -	Skin Irrit. 2; H315 Skin Sens. 1; H317 Aquatic Chronic 2; H411	7 - 13
1,4-Bis(2,3- epoxypropoxy)butane	2425-79-8 219-371-7 01-2119494060-45	Acute Tox. 4; H302 Acute Tox. 4; H332 Acute Tox. 4; H312 Skin Irrit. 2; H315 Eye Dam. 1; H318 Skin Sens. 1; H317 Aquatic Chronic 3; H412	1 - 3
Bis(2,3-epoxypropyl) terephthalate	7195-44-0 230-565-0 01-2119909640-43	Skin Irrit. 2; H315 Eye Dam. 1; H318 Skin Sens. 1; H317	1 - 3
Tris(oxiranylmethyl) benzene- 1,2,4-tricarboxylate	7237-83-4 230-638-7 01-2119912714-41	Eye Irrit. 2; H319 Skin Sens. 1; H317 Aquatic Chronic 2; H411	0.1 - 1

For explanation of abbreviations see section 16.

SECTION 4: First aid measures

4.1 Description of first aid measures

- | | |
|-------------------------|--|
| General advice | : Move out of dangerous area.
Consult a physician.
Show this safety data sheet to the doctor in attendance.
Do not leave the victim unattended. |
| If inhaled | : If unconscious place in recovery position and seek medical advice.
If symptoms persist, call a physician. |
| In case of skin contact | : If skin irritation persists, call a physician.
If on skin, rinse well with water.
If on clothes, remove clothes. |
| In case of eye contact | : Small amounts splashed into eyes can cause irreversible tissue damage and blindness. |

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

In the case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
Continue rinsing eyes during transport to hospital.
Remove contact lenses.
Protect unharmed eye.
Keep eye wide open while rinsing.
If eye irritation persists, consult a specialist.

If swallowed : Keep respiratory tract clear.
Do NOT induce vomiting.
Do not give milk or alcoholic beverages.
Never give anything by mouth to an unconscious person.
If symptoms persist, call a physician.
Take victim immediately to hospital.

4.2 Most important symptoms and effects, both acute and delayed

None known.

4.3 Indication of any immediate medical attention and special treatment needed

SECTION 5: Firefighting measures

5.1 Extinguishing media

Suitable extinguishing media : Use extinguishing measures that are appropriate to local circumstances and the surrounding environment.

Unsuitable extinguishing media : High volume water jet

5.2 Special hazards arising from the substance or mixture

Specific hazards during firefighting : Do not allow run-off from fire fighting to enter drains or water courses.

Hazardous combustion products : No data is available on the product itself.

5.3 Advice for firefighters

Special protective equipment for firefighters : Wear self-contained breathing apparatus for firefighting if necessary.

Specific extinguishing methods : No data is available on the product itself.

Further information : Collect contaminated fire extinguishing water separately. This must not be discharged into drains.
Fire residues and contaminated fire extinguishing water must be disposed of in accordance with local regulations.

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

SECTION 6: Accidental release measures

6.1 Personal precautions, protective equipment and emergency procedures

Personal precautions : Use personal protective equipment.

6.2 Environmental precautions

Environmental precautions : Prevent product from entering drains.
Prevent further leakage or spillage if safe to do so.
If the product contaminates rivers and lakes or drains inform respective authorities.

6.3 Methods and material for containment and cleaning up

Methods for cleaning up : Soak up with inert absorbent material (e.g. sand, silica gel, acid binder, universal binder, sawdust).
Keep in suitable, closed containers for disposal.

6.4 Reference to other sections

None

SECTION 7: Handling and storage

7.1 Precautions for safe handling

Advice on safe handling : Do not breathe vapours/dust.
Avoid exposure - obtain special instructions before use.
Avoid contact with skin and eyes.
For personal protection see section 8.
Smoking, eating and drinking should be prohibited in the application area.
To avoid spills during handling keep bottle on a metal tray.
Dispose of rinse water in accordance with local and national regulations.
Persons susceptible to skin sensitisation problems or asthma, allergies, chronic or recurrent respiratory disease should not be employed in any process in which this mixture is being used.
Sudden Release of Pressure Hazard

Advice on protection against fire and explosion : Normal measures for preventive fire protection.

Hygiene measures : When using do not eat or drink. When using do not smoke.
Wash hands before breaks and at the end of workday.

7.2 Conditions for safe storage, including any incompatibilities

Requirements for storage areas and containers : Keep container tightly closed in a dry and well-ventilated place. Containers which are opened must be carefully resealed and kept upright to prevent leakage. Electrical installations / working materials must comply with the technological safety standards.

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Advice on common storage : Strong acids
Strong bases
Strong oxidizing agents

Recommended storage temperature : 2 - 40 °C

Other data : No decomposition if stored and applied as directed.

7.3 Specific end use(s)

SECTION 8: Exposure controls/personal protection

8.1 Control parameters

Not applicable

Derived No Effect Level (DNEL) according to Regulation (EC) No. 1907/2006:

Substance name	End Use	Exposure routes	Potential health effects	Value
Bisphenol A epoxy resin	Workers	Dermal	Systemic effects, Short-term exposure	8.33 mg/kg bw/day
	Workers	Inhalation	Systemic effects, Short-term exposure	12.25 mg/m3
	Workers	Dermal	Systemic effects, Long-term exposure	8.33 mg/kg bw/day
	Workers	Inhalation	Systemic effects, Long-term exposure	12.25 mg/m3
	Consumers	Dermal	Systemic effects, Short-term exposure	3.571 mg/kg bw/day
	Consumers	Oral	Systemic effects, Short-term exposure	0.75 mg/kg bw/day
	Consumers	Dermal	Systemic effects, Long-term exposure	3.571 mg/kg bw/day
	Consumers	Oral	Systemic effects, Long-term exposure	0.75 mg/kg bw/day
terephthalic acid diglycidylester	Workers	Dermal	Systemic effects, Long-term exposure	2 mg/kg bw/day
	Workers	Inhalation	Systemic effects, Long-term exposure	14 mg/m3
	Consumers	Dermal	Systemic effects, Long-term exposure	1 mg/kg bw/day
	Consumers	Inhalation	Systemic effects, Long-term exposure	3.5 mg/m3
	Consumers	Oral	Systemic effects, Long-term exposure	1 mg/kg bw/day
	Workers	Dermal	Systemic effects,	1.25 mg/kg

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version 1.0 Revision Date: 03.06.2016 SDS Number: 400001015910 Date of last issue: -
 Date of first issue: 03.06.2016

triglycidylester			Long-term exposure	bw/day
	Consumers	Dermal	Systemic effects, Long-term exposure	0.62 mg/kg bw/day
	Consumers	Inhalation	Systemic effects, Long-term exposure	2.18 mg/m3
	Workers	Inhalation	Systemic effects, Long-term exposure	8.75 mg/m3
	Consumers	Oral	Systemic effects, Long-term exposure	0.62 mg/kg bw/day

Predicted No Effect Concentration (PNEC) according to Regulation (EC) No. 1907/2006:

Substance name	Environmental Compartment	Value
Bisphenol A epoxy resin	Fresh water	0.006 mg/l
Remarks:	Assessment Factors	
	Marine water	0.0006 mg/l
	Assessment Factors	
	Freshwater - intermittent	0.018 mg/l
	Assessment Factors	
	Fresh water sediment	0.996 mg/kg
	Equilibrium method	
	Marine sediment	0.0996 mg/kg
	Equilibrium method	
	Soil	0.196 mg/kg
	Equilibrium method	
	Sewage treatment plant	10 mg/l
	Assessment Factors	
	Secondary Poisoning	11 mg/kg
terephthalic acid diglycidylester	Fresh water	0.00294 mg/l
	Assessment Factors	
	Marine water	0.00029 mg/l
	Assessment Factors	
	Freshwater - intermittent	0.0294 mg/l
	Assessment Factors	
	Sewage treatment plant	1.86 mg/l
	Assessment Factors	
	Fresh water sediment	0.00869 mg/kg
	Equilibrium method	

ARALDITE® 2014-1 GB RESIN

Version 1.0 Revision Date: 03.06.2016 SDS Number: 400001015910 Date of last issue: -
Date of first issue: 03.06.2016

	Marine sediment	0.00087 mg/kg
	Equilibrium method	
	Soil	0.00553 mg/kg
	Equilibrium method	
trimellitic acid triglycidylester	Fresh water	0.0067 mg/l
	Assessment Factors	
	Marine water	0.0067 mg/l
	Assessment Factors	
	Freshwater - intermittent	0.067 mg/l
	Assessment Factors	
	Sewage treatment plant	2.89 mg/l
	Assessment Factors	
	Sediment	0.0418 mg/kg
	Equilibrium method	
	Marine sediment	0.00418 mg/kg
	Equilibrium method	
	Soil	0.0305 mg/kg
	Equilibrium method	

8.2 Exposure controls

Personal protective equipment

Eye protection : Eye wash bottle with pure water
Tightly fitting safety goggles
Wear face-shield and protective suit for abnormal processing problems.

Hand protection

Material : butyl-rubber

Material : Ethyl Vinyl Alcohol Laminate (EVAL)
Break through time : > 8 h

Material : Nitrile rubber

Material : Neoprene rubber
Break through time : 10 - 480 min

Remarks : The suitability for a specific workplace should be discussed with the producers of the protective gloves. Take note of the information given by the producer concerning permeability and break through times, and of special workplace conditions (mechanical strain, duration of contact).

Skin and body protection : Impervious clothing

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Choose body protection according to the amount and concentration of the dangerous substance at the work place.

Respiratory protection : Use respiratory protection unless adequate local exhaust ventilation is provided or exposure assessment demonstrates that exposures are within recommended exposure guidelines.
Recommended Filter type:
Combined particulates and organic vapour type

Filter type : Filter type A-P

SECTION 9: Physical and chemical properties

9.1 Information on basic physical and chemical properties

Appearance	: liquid
Colour	: beige
Odour	: slight
pH	: ca. 7 Concentration: 500 g/l (20 °C)
Melting point/freezing point	: No data available
Boiling point/boiling range	: > 200 °C
Flash point	: > 100 °C Method: closed cup
Vapour pressure	: < 1.33 hPa (20 °C)
Density	: 1.6 g/cm ³ (25 °C)
Solubility(ies) Water solubility	: practically insoluble (20 °C)
Auto-ignition temperature	: does not ignite
Decomposition temperature	: > 200 °C
Viscosity Viscosity, dynamic	: 92,800 mPa.s (25 °C) Method: Other guidelines

9.2 Other information

No data available

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

SECTION 10: Stability and reactivity

10.1 Reactivity

No decomposition if stored and applied as directed.

10.2 Chemical stability

No decomposition if stored and applied as directed.

10.3 Possibility of hazardous reactions

Hazardous reactions : No decomposition if stored and applied as directed.

10.4 Conditions to avoid

Conditions to avoid : No data available

10.5 Incompatible materials

Materials to avoid : No data available

10.6 Hazardous decomposition products

Carbon oxides

Burning produces noxious and toxic fumes.

SECTION 11: Toxicological information

11.1 Information on toxicological effects

Acute toxicity

Acute oral toxicity - Product : Acute toxicity estimate : > 2,000 mg/kg
Method: Calculation method

Acute inhalation toxicity - Product : Acute toxicity estimate : > 20 mg/l
Exposure time: 4 h
Test atmosphere: vapour
Method: Calculation method

Acute dermal toxicity - Product : Acute toxicity estimate : > 2,000 mg/kg
Method: Calculation method

Acute toxicity (other routes of administration) : No data available

Skin corrosion/irritation

Components:

Bisphenol A epoxy resin:

Species: Rabbit

Assessment: Mild skin irritant

Method: OECD Test Guideline 404

Result: Irritating to skin.

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

bisphenol F-epoxy resin:

Species: Rabbit

Method: OECD Test Guideline 404

Result: Irritating to skin.

Butanedioldiglycidyl ether:

Species: Rabbit

Method: OECD Test Guideline 404

Result: Skin irritation

terephthalic acid diglycidylester:

Species: Rabbit

Assessment: Mild skin irritant

Result: Normally reversible injuries

trimellitic acid triglycidylester:

Species: Rabbit

Assessment: No skin irritation

Method: OECD Test Guideline 404

Result: No skin irritation

Serious eye damage/eye irritation

Components:

Bisphenol A epoxy resin:

Species: Rabbit

Assessment: Mild eye irritant

Method: OECD Test Guideline 405

Result: Irritating to eyes.

bisphenol F-epoxy resin:

Species: Rabbit

Method: OECD Test Guideline 405

Result: No eye irritation

Butanedioldiglycidyl ether:

Species: Rabbit

Method: OECD Test Guideline 405

Result: Risk of serious damage to eyes.

terephthalic acid diglycidylester:

Species: Rabbit

Assessment: Corrosive

Result: Irreversible effects on the eye

trimellitic acid triglycidylester:

Species: Rabbit

Assessment: Irritant

Method: OECD Test Guideline 405

Result: Normally reversible injuries

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Respiratory or skin sensitisation

Components:

Bisphenol A epoxy resin:

Exposure routes: Skin

Species: Mouse

Assessment: May cause sensitisation by skin contact.

Method: OECD Test Guideline 429

Result: Causes sensitisation.

bisphenol F-epoxy resin:

Exposure routes: Skin

Species: Mouse

Method: OECD Test Guideline 429

Result: May cause sensitisation by skin contact.

Butanedioldiglycidyl ether:

Exposure routes: Skin

Species: Guinea pig

Method: OECD Test Guideline 406

Result: May cause sensitisation by skin contact.

terephthalic acid diglycidylester:

Exposure routes: Skin

Species: Guinea pig

Method: OECD Test Guideline 406

Result: Causes sensitisation.

trimellitic acid triglycidylester:

Exposure routes: Skin

Species: Guinea pig

Method: OECD Test Guideline 406

Result: Causes sensitisation.

Assessment: No data available

Germ cell mutagenicity

Components:

Bisphenol A epoxy resin:

Genotoxicity in vitro

: Metabolic activation: with and without metabolic activation

Method: OECD Test Guideline 476

Result: positive

: Concentration: 0 - 5000 ug/plate

Metabolic activation: with and without metabolic activation

Method: OECD Test Guideline 471

Result: positive

bisphenol F-epoxy resin:

Genotoxicity in vitro

: Metabolic activation: with and without metabolic activation

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Method: OECD Test Guideline 471
Result: positive

: Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 473
Result: positive

: Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 476
Result: positive

Butanedioldiglycidyl ether:
Genotoxicity in vitro

: Concentration: 10 - 5000 ug/plate
Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 471
Result: positive

: Concentration: 1 - 100 µg/L
Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 473
Result: positive

terephthalic acid diglycidylester:
Genotoxicity in vitro

: Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 476
Result: positive

: Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 471
Result: positive

trimellitic acid triglycidylester:
Genotoxicity in vitro

: Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 476
Result: positive

: Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 471
Result: positive

Components:

Bisphenol A epoxy resin:
Genotoxicity in vivo

: Cell type: Germ
Application Route: Oral

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Method: OECD Test Guideline 478
Result: negative

Cell type: Somatic
Application Route: Oral
Dose: 0 - 5000 mg/kg
Method: OPPTS 870.5395
Result: negative

bisphenol F-epoxy resin:
Genotoxicity in vivo

: Cell type: Somatic
Application Route: Oral
Exposure time: 48 h
Dose: 2000 mg/kg
Method: OECD Test Guideline 474
Result: negative

Cell type: Somatic
Application Route: Oral
Dose: 2000 mg/kg
Method: OECD Test Guideline 486
Result: negative

Butanedioldiglycidyl ether:
Genotoxicity in vivo

: Test Type: In vivo micronucleus test
Test species: Mouse
Cell type: Somatic
Application Route: Oral
Exposure time: 4 d
Dose: 187.5 - 750 mg/kg
Method: OECD Test Guideline 474
Result: negative

Test Type: unscheduled DNA synthesis assay
Test species: Rat
Cell type: Liver cells
Application Route: Oral
Method: OECD Test Guideline 486
Result: negative

terephthalic acid diglycidylester:
Genotoxicity in vivo

: Application Route: Oral
Method: OECD Test Guideline 483
Result: negative

Application Route: Oral
Method: OECD Test Guideline 474

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Result: negative

trimellitic acid triglycidylester:
Genotoxicity in vivo

: Application Route: Oral
Method: OECD Test Guideline 483
Result: negative

Application Route: Oral
Method: OECD Test Guideline 474
Result: negative

Components:

Bisphenol A epoxy resin:
Germ cell mutagenicity-
Assessment

: Weight of evidence does not support classification as a germ cell mutagen.

Butanedioldiglycidyl ether:
Germ cell mutagenicity-
Assessment

: Weight of evidence does not support classification as a germ cell mutagen.

Germ cell mutagenicity-
Assessment

: No data available

Carcinogenicity

Components:

Bisphenol A epoxy resin:
Species: Rat, (male and female)
Application Route: Oral
Exposure time: 24 month(s)
Dose: 15 mg/kg
Frequency of Treatment: 7 days/week
Method: OECD Test Guideline 453
Result: negative

Species: Mouse, (male)
Application Route: Dermal
Exposure time: 24 month(s)
Dose: 0.1 mg/kg
Frequency of Treatment: 3 days/week
Method: OECD Test Guideline 453
Result: negative

Species: Rat, (female)
Application Route: Dermal
Exposure time: 24 month(s)
Dose: 1 mg/kg
Frequency of Treatment: 5 days/week

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Method: OECD Test Guideline 453
Result: negative

Carcinogenicity - Assessment : No data available

Reproductive toxicity

Components:

Bisphenol A epoxy resin:
Effects on fertility

: Test Type: Two-generation study
Species: Rat, male and female
Application Route: Oral
Dose: >750 milligram per kilogram
General Toxicity - Parent: No-observed-effect level: 540 mg/kg body weight
General Toxicity F1: No-observed-effect level: 540 mg/kg body weight
Symptoms: No adverse effects
Method: OECD Test Guideline 416
Result: No effects on fertility and early embryonic development were detected.

bisphenol F-epoxy resin:

Species: Rat, male and female
Application Route: Oral
Method: OECD Test Guideline 416
Result: No effects on fertility and early embryonic development were detected.

Components:

Bisphenol A epoxy resin:
Effects on foetal development

: Species: Rabbit, female
Application Route: Dermal
General Toxicity Maternal: No observed adverse effect level: 30 mg/kg body weight
Method: Other guidelines
Result: No teratogenic effects

Species: Rabbit, female
Application Route: Oral
General Toxicity Maternal: No observed adverse effect level: 60 mg/kg body weight
Method: OECD Test Guideline 414
Result: No teratogenic effects

Species: Rat, female
Application Route: Oral
General Toxicity Maternal: No observed adverse effect level: 180 mg/kg body weight
Method: OECD Test Guideline 414
Result: No teratogenic effects

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

bisphenol F-epoxy resin:

Species: Rabbit, female
Application Route: Dermal
General Toxicity Maternal: No observed adverse effect level:
30 mg/kg body weight
Result: No teratogenic effects

Reproductive toxicity - : No data available
Assessment

STOT - single exposure

No data available

STOT - repeated exposure

No data available

Repeated dose toxicity

Components:

Bisphenol A epoxy resin:

Species: Rat, male and female

NOAEL: 50 mg/kg

Application Route: Ingestion

Exposure time: 14 WeeksNumber of exposures: 7 d

Method: Subchronic toxicity

Species: Rat, male and female

NOEL: 10 mg/kg

Application Route: Skin contact

Exposure time: 13 WeeksNumber of exposures: 5 d

Method: Subchronic toxicity

Species: Mouse, male

NOAEL: 100 mg/kg

Application Route: Skin contact

Exposure time: 13 WeeksNumber of exposures: 3 d

Method: Subchronic toxicity

bisphenol F-epoxy resin:

Species: Rat, male and female

NOAEL: 250 mg/kg

Application Route: Ingestion

Exposure time: 13 WeeksNumber of exposures: 7 d

Method: Subchronic toxicity

Butanedioldiglycidyl ether:

Species: Rat, male and female

NOAEL: 200 mg/kg

Application Route: Ingestion

Exposure time: 28 dNumber of exposures: 7 d

Method: Subacute toxicity

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

terephthalic acid diglycidylester:

Species: Rat, male and female

NOAEL: > 240 mg/kg

Application Route: Ingestion

Exposure time: 672 hNumber of exposures: 7 d

Method: Subacute toxicity

trimellitic acid triglycidylester:

Species: Rat, male

NOAEL: 150

Application Route: Ingestion

Exposure time: 672 hNumber of exposures: 7 d

Method: Subacute toxicity

Species: Rat, female

NOAEL: >= 500

Application Route: Ingestion

Exposure time: 672 hNumber of exposures: 7 d

Method: Subacute toxicity

Repeated dose toxicity - : No data available
Assessment

Aspiration toxicity

No data available

Experience with human exposure

General Information: No data available

Inhalation: No data available

Skin contact: No data available

Eye contact: No data available

Ingestion: No data available

Toxicology, Metabolism, Distribution

No data available

Neurological effects

No data available

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Further information

Ingestion: No data available

SECTION 12: Ecological information

12.1 Toxicity

Components:

Bisphenol A epoxy resin:

Toxicity to fish : LC50 (Oncorhynchus mykiss (rainbow trout)): 1.5 mg/l
Exposure time: 96 h
Test Type: static test
Test substance: Fresh water
Method: OECD Test Guideline 203

Toxicity to daphnia and other aquatic invertebrates : EC50 (Daphnia magna (Water flea)): 2.7 mg/l
Exposure time: 48 h
Test Type: static test
Test substance: Fresh water

Toxicity to algae : EC50 (Selenastrum capricornutum (green algae)): 9.4 mg/l
Exposure time: 72 h
Test Type: static test
Test substance: Fresh water
Method: EPA-660/3-75-009

Toxicity to bacteria : IC50 (activated sludge): > 100 mg/l
Exposure time: 3 h
Test Type: static test
Test substance: Fresh water

Toxicity to daphnia and other aquatic invertebrates (Chronic toxicity) : NOEC: 0.3 mg/l
Exposure time: 21 d
Species: Daphnia magna (Water flea)
Test Type: semi-static test
Test substance: Fresh water
Method: OECD Test Guideline 211

bisphenol F-epoxy resin:

Toxicity to fish : LC50 (Oncorhynchus mykiss (rainbow trout)): 0.55 mg/l
Exposure time: 96 h
Test Type: semi-static test
Test substance: Fresh water
Method: OECD Test Guideline 203

Toxicity to daphnia and other aquatic invertebrates : EC50 (Daphnia magna (Water flea)): 1.6 mg/l
Exposure time: 48 h
Test Type: static test
Test substance: Fresh water
Method: OECD Test Guideline 202

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Toxicity to algae : EC50 (Selenastrum capricornutum (green algae)): 1.8 mg/l
Exposure time: 72 h
Test Type: static test
Test substance: Fresh water
Method: OECD Test Guideline 201

Toxicity to bacteria : IC50 (activated sludge): > 100 mg/l
Exposure time: 3 h
Test Type: static test
Test substance: Fresh water

Toxicity to daphnia and other aquatic invertebrates (Chronic toxicity) : NOEC: 0.3 mg/l
Exposure time: 21 d
Species: Daphnia magna (Water flea)
Test Type: semi-static test
Test substance: Fresh water
Method: OECD Test Guideline 211

Ecotoxicology Assessment
Acute aquatic toxicity : This product has no known ecotoxicological effects.

Chronic aquatic toxicity : Toxic to aquatic life with long lasting effects.

Butanedioldiglycidyl ether:

Toxicity to fish : LC50 (Brachydanio rerio (zebrafish)): 24 mg/l
Exposure time: 96 h
Test Type: static test
Test substance: Fresh water
Method: OECD Test Guideline 203

Toxicity to daphnia and other aquatic invertebrates : EC50 (Daphnia magna (Water flea)): 75 mg/l
Exposure time: 24 h
Test Type: static test
Test substance: Fresh water
Method: OECD Test Guideline 202

Toxicity to algae : EL50 : > 160 mg/l
Exposure time: 72 h
Test Type: static test
Test substance: Fresh water
Method: OECD Test Guideline 201

Toxicity to bacteria : IC50 (activated sludge): > 100 mg/l
Exposure time: 3 h
Test Type: static test
Test substance: Fresh water
Method: OECD Test Guideline 209

terephthalic acid diglycidylester:

Toxicity to fish : LC50 : 8.8 mg/l
Exposure time: 96 h
Test Type: static test

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

	Test substance: Fresh water Method: OECD Test Guideline 203
Toxicity to daphnia and other aquatic invertebrates	: EC50 (Daphnia magna (Water flea)): 81 mg/l Exposure time: 48 h Test Type: static test Test substance: Fresh water Method: OECD Test Guideline 202
Toxicity to algae	: ErC50 (Selenastrum capricornutum (green algae)): 2.94 mg/l Exposure time: 72 h Test Type: static test Test substance: Fresh water Method: OECD Test Guideline 201
trimellitic acid triglycidylester:	
Toxicity to fish	: LC50 (Oncorhynchus mykiss (rainbow trout)): > 6.7 mg/l Exposure time: 96 h Test Type: semi-static test Test substance: Fresh water Method: OECD Test Guideline 203
Toxicity to daphnia and other aquatic invertebrates	: EC50 (Daphnia magna (Water flea)): 21.7 mg/l Exposure time: 48 h Test Type: semi-static test Test substance: Fresh water Method: OECD Test Guideline 202
Toxicity to algae	: EC50 (Selenastrum capricornutum (green algae)): 27.45 mg/l Exposure time: 72 h Test Type: static test Test substance: Fresh water Method: OECD Test Guideline 201
Toxicity to bacteria	: EC50 (activated sludge): > 1,000 mg/l Exposure time: 3 h Test substance: brackish water Method: OECD Test Guideline 209

12.2 Persistence and degradability

Components:

Bisphenol A epoxy resin:

Biodegradability : Inoculum: Sewage (STP effluent)
Concentration: 20 mg/l
Result: Not readily biodegradable.
Biodegradation: 5 %
Exposure time: 28 d
Method: OECD Test Guideline 301F

Stability in water : Degradation half life (DT50): 4.83 d (25 °C) pH: 4
Method: OECD Test Guideline 111
GLP: yes

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Remarks: Fresh water

Degradation half life (DT50): 7.1 d (25 °C) pH: 9
Method: OECD Test Guideline 111
GLP: yes
Remarks: Fresh water

Degradation half life (DT50): 3.58 d (25 °C) pH: 7
Method: OECD Test Guideline 111
GLP: yes
Remarks: Fresh water

bisphenol F-epoxy resin:

Biodegradability : Inoculum: activated sludge
Concentration: 3 mg/l
Result: Not readily biodegradable.
Biodegradation: ca. 0 %
Exposure time: 28 d
Method: Directive 67/548/EEC Annex V, C.4.E.

Butanedioldiglycidyl ether:

Biodegradability : Inoculum: activated sludge
Concentration: 20 mg/l
Result: Not readily biodegradable.
Biodegradation: 43 %
Exposure time: 28 d
Method: OECD Test Guideline 301F

terephthalic acid diglycidylester:

Stability in water : Degradation half life (DT50): 118.26 hrs (20 °C) pH: 7
Method: OECD Test Guideline 111
GLP: yes
Remarks: Fresh water

trimellitic acid triglycidylester:

Biodegradability : Inoculum: Fresh water
Result: Not readily biodegradable.
Biodegradation: 59 %
Exposure time: 28 d
Method: OECD Test Guideline 301F

Stability in water

: Degradation half life (DT50): 101.91 hrs (20 °C) pH: 4
Method: OECD Test Guideline 111
GLP: yes
Remarks: Fresh water

12.3 Bioaccumulative potential

Components:

Bisphenol A epoxy resin:

Bioaccumulation : Bioconcentration factor (BCF): 31
Remarks: Does not bioaccumulate.

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

Partition coefficient: n-octanol/water : log Pow: 3.242 (25 °C)
pH: 7.1
Method: OECD Test Guideline 117

bisphenol F-epoxy resin:
Bioaccumulation : Species: Fish
Bioconcentration factor (BCF): 150
Remarks: Does not bioaccumulate.

Partition coefficient: n-octanol/water : log Pow: 2.7 - 3.6
Method: OECD Test Guideline 117

Butanedioldiglycidyl ether:
Partition coefficient: n-octanol/water : log Pow: -0.269 (25 °C)
pH: 6.7
Method: OECD Test Guideline 117

terephthalic acid diglycidylester:
Partition coefficient: n-octanol/water : log Pow: 1.7 (25 °C)
Method: OECD Test Guideline 117
GLP: yes

trimellitic acid triglycidylester:
Partition coefficient: n-octanol/water : log Pow: 0.9 (25 °C)
Method: OECD Test Guideline 117

12.4 Mobility in soil

Components:

Bisphenol A epoxy resin:
Distribution among environmental compartments : Koc: 445

bisphenol F-epoxy resin:
Distribution among environmental compartments : Koc: 4460Method: OECD Test Guideline 121

Butanedioldiglycidyl ether:
Distribution among environmental compartments : Koc: 12.59Method: OECD Test Guideline 121

terephthalic acid diglycidylester:
Distribution among environmental compartments : Koc: 2Method: OECD Test Guideline 121

trimellitic acid triglycidylester:
Distribution among environmental compartments : Koc: 251Method: OECD Test Guideline 121

12.5 Results of PBT and vPvB assessment

Product:

Assessment : This substance/mixture contains no components considered

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

to be either persistent, bioaccumulative and toxic (PBT), or very persistent and very bioaccumulative (vPvB) at levels of 0.1% or higher..

12.6 Other adverse effects

Product:

Additional ecological information : An environmental hazard cannot be excluded in the event of unprofessional handling or disposal.
Toxic to aquatic life with long lasting effects.

SECTION 13: Disposal considerations

13.1 Waste treatment methods

Product : The product should not be allowed to enter drains, water courses or the soil.
Do not contaminate ponds, waterways or ditches with chemical or used container.
Send to a licensed waste management company.

Contaminated packaging : Empty remaining contents.
Dispose of as unused product.
Do not re-use empty containers.

SECTION 14: Transport information

IATA

14.1 UN number : UN 3082
14.2 UN proper shipping name : Environmentally hazardous substance, liquid, n.o.s.
(BISPHENOL A EPOXY RESIN, BISPHENOL F EPOXY RESIN)

14.3 Transport hazard class(es) : 9
14.4 Packing group : III
Labels : Miscellaneous
Packing instruction (cargo aircraft) : 964
Packing instruction (passenger aircraft) : 964

IMDG

14.1 UN number : UN 3082
14.2 UN proper shipping name : ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S.
(BISPHENOL A EPOXY RESIN, BISPHENOL F EPOXY RESIN)
14.3 Transport hazard class(es) : 9

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

14.4 Packing group : III
Labels : 9
EmS Code : F-A, S-F
14.5 Environmental hazards
Marine pollutant : yes

ADR

14.1 UN number : UN 3082
14.2 UN proper shipping name : ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S.
(BISPHENOL A EPOXY RESIN, BISPHENOL F EPOXY RESIN)
14.3 Transport hazard class(es) : 9
14.4 Packing group : III
Labels : 9
14.5 Environmental hazards
Marine pollutant : no

RID

14.1 UN number : UN 3082
14.2 UN proper shipping name : ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S.
(BISPHENOL A EPOXY RESIN, BISPHENOL F EPOXY RESIN)
14.3 Transport hazard class(es) : 9
14.4 Packing group : III
Labels : 9
14.5 Environmental hazards
Marine pollutant : yes

Transport in bulk according to Annex II of Marpol and the IBC Code

Not applicable for product as supplied.

SECTION 15: Regulatory information

15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

REACH - Candidate List of Substances of Very High Concern for Authorisation (Article 59) : Not applicable

REACH - List of substances subject to authorisation (Annex XIV) : Not applicable

The components of this product are reported in the following inventories:

TSCA : Not On TSCA Inventory

DSL : This product contains the following components that are not on the Canadian DSL nor NDSL.

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

AICS	: Low volume exemption
NZIoC	: On the inventory, or in compliance with the inventory
ENCS	: Low volume exemption
KECI	: Not in compliance with the inventory
PICCS	: Not in compliance with the inventory
IECSC	: Low volume exemption

Inventories

AICS (Australia), DSL (Canada), IECSC (China), ENCS (Japan), KECI (Korea), NZIOIC (New Zealand), PICCS (Philippines), TCSI (Taiwan), TSCA (United States of America)

15.2 Chemical safety assessment

SECTION 16: Other information

Full text of H-Statements

H302	: Harmful if swallowed.
H312	: Harmful in contact with skin.
H315	: Causes skin irritation.
H317	: May cause an allergic skin reaction.
H318	: Causes serious eye damage.
H319	: Causes serious eye irritation.
H332	: Harmful if inhaled.
H411	: Toxic to aquatic life with long lasting effects.
H412	: Harmful to aquatic life with long lasting effects.

Full text of other abbreviations

Acute Tox.	: Acute toxicity
Aquatic Chronic	: Chronic aquatic toxicity
Eye Dam.	: Serious eye damage
Eye Irrit.	: Eye irritation
Skin Irrit.	: Skin irritation
Skin Sens.	: Skin sensitisation

Further information

SAFETY DATA SHEET

according to Regulation (EC) No. 1907/2006

HUNTSMAN

Enriching lives through innovation

ARALDITE® 2014-1 GB RESIN

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	03.06.2016	400001015910	Date of first issue: 03.06.2016

While the information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, EXPRESS OR OTHERWISE.

IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

THE PRODUCT MAY PRESENT HAZARDS AND SHOULD BE USED WITH CAUTION. WHILE CERTAIN HAZARDS ARE DESCRIBED IN THIS PUBLICATION, NO GUARANTEE IS MADE THAT THESE ARE THE ONLY HAZARDS THAT EXIST.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent upon the manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

The trademarks above are the property of Huntsman Corporation or an affiliate thereof.

NO PERSON OR ORGANIZATION EXCEPT A DULY AUTHORIZED HUNTSMAN EMPLOYEE IS AUTHORIZED TO PROVIDE OR MAKE AVAILABLE DATA SHEETS FOR HUNTSMAN PRODUCTS. DATA SHEETS FROM UNAUTHORIZED SOURCES MAY CONTAIN INFORMATION THAT IS NO LONGER CURRENT OR ACCURATE.